

FICHA TÉCNICA: TUBO AISLANTE FIBRA VIDRIO CON SILICONA Alta Temperatura anti fuego



Manguito de fibra de vidrio impregnado con silicona. Resistente para proteger diferentes tipos de mangueras, alambres y cables de los peligros de las altas temperaturas y de la llama ocasional. Buen aislamiento térmico, a prueba de fuego.

Temperatura continua: -70°C a 260°C

Temperatura corto plazo: 1000°C 15-20 minutos

Temperatura corto plazo: 1.650°C 15-30 segundos

Excelente resistencia a la abrasión

ISO 9001 . 2008 CE , DIN 5510-2 (fire and smoke toxicity testing), RoHS, MSDS EN45545-2, R22.

Resistente al fuego, aislamiento, anti envejecimiento, evita salpicaduras de hierro fundido, resistente a la abrasión, resistente al agua, al aceite, resistente a ácidos y álcalis.

Test Requested:

EN 60332-1-2:2004+A11:2016 Tests on electric and optical fibre cables under fire conditions



Property	Value
Tensile Strength	8,2 Mpa
Peeling intensity	200
	300%
Rate voltage	7kv – 25kv
	300 4 hours No crack according to ASTM D 2671
	-75 4 hours No crack according to ASTM D 2671
2.Tensile strength	10.3 Mpa according to ASTM D 638
3. Thermal conductivity	0,035 W/m·K for Fiberglass and 0.27 W/m·K for Silicon rubber.No exact Thermal conductivity data for Fire Sleeve